

TuskXC2700T / Tusk2700W

	Units	ASTM#	Range
Density	g/cm ³		1.18 – 1.2
Tensile Modulus	MPa	D638M	2650 – 2880
Tensile Strength	MPa	D638M	47.1 – 53.6
Elongation at Break	%	D638M	11 – 20
Flexural Modulus	MPa	D790M	2040 – 2370
Flexural Strength	MPa	D790M	63.1 – 74.16
Notched Izod Impact	J/m	D256A	20 – 30
Hardness	Shore D	D2240	81
Heat Deflection Temp (0.46 MPa)	°C	D648 - 98c	45.9 – 54.5
Heat Deflection Temp (1.81 MPa)	°C	D648 - 98c	49.0 – 49.7
Colour	Transparent or white		
	Actual values may vary with build conditions		

- ✓ Transparent (TuskXC2700T)
- ✓ Strong
- ✓ Water resistant
- ✓ Durable

- ✓ Functional prototypes
- ✓ Wind tunnel testing
- ✓ Water flow analysis
- ✓ High-end finished models
- ✓ ABS-like parts